



ELRIM Cycloaliphatic Epoxy Provides:

- Nontracking, self-scouring, nonweathering performance
- Superior dielectric strength, dielectric loss and power factor
- Choice of shapes allows design innovation
- Mechanical and thermal toughness
- Shatter free arc flashover performance
- Oil resistant

Elliott Design Provides:

- Thermal cycling withstand from +200° F to -200° F
- High strength - field proven performance
- Experience with cycloaliphatic epoxy since 1975

Important:

Water that accumulates in the inserts and then freezes will damage epoxy insulators. When insulators are to be installed outdoors, inserts must be partially filled with no-oxide compound (or similar material) to prevent moisture accumulation in the inserts.

Ratings and Dimensions of Apparatus Insulator

Catalog Number	Nominal Voltage kV	Dimensions Inches				Compression Pounds	Net Weight Pounds
		"A"	"B"	"C"	"D"		
2950-201.5	0.6	4	1.5	2	1.375	20,000	0.93



Apparatus Insulators
Indoor - Outdoor
Special Bolt Series 0.375"-16 Inserts

Descriptive
Bulletin
2950
Page 2 2015

If you do not find the design

you need

PLEASE CONTACT

our REPRESENTATIVE or the FACTORY